Australian Standard[™]

Method for the qualitative identification of asbestos in bulk samples



This Australian Standard was prepared by Committee CH-031, Methods for the Examination of Workplace Atmospheres. It was approved on behalf of the Council of Standards Australia on 20 February 2004 and published on 24 March 2004.

The following are represented on Committee CH-031:

Australian Aluminium Council Australian Chamber of Commerce and Industry Australian Institute of Occupational Hygienists Australian Mines and Metals Association Bureau of Steel Manufacturers of Australia Clean Air Society of Australia and New Zealand Coal Services Commonwealth Department of Health and Aged Care Department of Administrative and Information Services, SA Department of Consumer and Employment Protection, Worksafe Division, WA Department of Mineral Resources, NSW National Association of Testing Authorities Australia WorkCover New South Wales

Keeping Standards up-to-date

Standards are living documents which reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued. Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments which may have been published since the Standard was purchased.

Detailed information about Standards can be found by visiting the Standards Web Shop at www.standards.com.au and looking up the relevant Standard in the on-line catalogue.

Alternatively, the printed Catalogue provides information current at 1 January each year, and the monthly magazine, *The Global Standard*, has a full listing of revisions and amendments published each month.

Australian Standards[™] and other products and services developed by Standards Australia are published and distributed under contract by SAI Global, which operates the Standards Web Shop.

We also welcome suggestions for improvement in our Standards, and especially encourage readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at mail@standards.org.au, or write to the Chief Executive, Standards Australia International Ltd, GPO Box 5420, Sydney, NSW 2001.

This Standard was issued in draft form for comment as DR 02125.

Australian Standard[™]

Method for the qualitative identification of asbestos in bulk samples

First published as AS 4964-2004.

COPYRIGHT

© Standards Australia International

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia International Ltd GPO Box 5420, Sydney, NSW 2001, Australia ISBN 0 7337 5851 7

PREFACE

This Standard was prepared by Standards Australia Committee CH-031 Methods for the Examination of Workplace Atmospheres from a NATA Guidance Note - *Identification of Asbestos in Bulk Samples* compiled by NATA's Occupational Hygiene Technical Group.

The Standard describes polarized light microscopy (PLM) as the primary technique for identification because of its simplicity, low cost, relevance and detection limits. The determination of principal refractive indices by dispersion staining (DS) on its own is not sufficient and needs to be used in conjunction with various other optical properties using PLM.

The Standard sets out relatively simple aspects of sample preparation and PLM that enable a large proportion of commercial samples to be identified, even though some samples will be difficult or impossible to analyze. These samples may require the use of an independent confirming technique such as infrared spectroscopy, X-ray diffraction, scanning electron microscopy or transmission electron microscopy, if PLM fails to give an unequivocal identification, or they require more complex sample preparation.

The Committee considers analysts inexperienced in asbestos identification should not undertake work in this area without making personal contact with an experienced occupational hygienist or analyst to obtain training in the technique involved. Internal and external quality assurance testing should be used to help ensure the continuing competency of analysts.

The procedure has the following known limitations:

- (a) PLM is a qualitative technique only.
- (b) It does not cover the identification of airborne and water-borne asbestos.
- (c) Most samples of tremolite, actinolite and anthophyllite show a wide range of optical properties and can not be equivocally identified by PLM and dispersion staining.
- (d) For valid asbestos identification there must be sufficient sample of the unknown fibres for them to exceed the practical detection limit of the technique used. To report 'trace' levels using confirming techniques the fibres must be observed at 'trace' levels by PLM, because of the difference in detection limits between the techniques. Appendix A discusses some of these differences.

The United Kingdom Health and Safety Executive (HSE) Method for the Determination of Hazardous Substances (MDHS77, June 1994), 'Asbestos in Bulk Materials - Sampling and Identification by Polarized Light Microscopy', can be used for guidance. Refer to Appendix B for minor adaptations for Australian conditions that should be applied to MDHS77, as well as additional techniques comments on the technique.

No attempt has been made in the Standard to quantify the amount of asbestos present apart from the descriptive terms 'asbestos detected', 'trace asbestos detected' or 'no asbestos detected'. The Committee considered that quantification of the technique would not be practicable, and not required in most situations. More complicated analysis may be prohibitively costly without yielding any more practical information. It was considered the qualitative terms would be sufficient for a risk assessment to be made.

This Standard incorporates principles set out in the NATA publication ISO/IEC 17025 Application Document, Supplementary Requirements for Accreditation in the Field of Chemical Testing.

The term 'informative' has been used in this Standard to define the application of the appendix to which it applies. An 'informative' appendix is only for information and guidance.

CONTENTS

Page

1	SCOPE	. 4
2	OBJECTIVE	. 4
3	REFERENCED DOCUMENTS	. 4
4	DEFINITIONS	. 4
5	REAGENTS	. 6
6	APPARATUS	. 6
7	SAMPLING	. 6
8	PROCEDURE FOR BULK SAMPLE IDENTIFICATION	. 7
9	TEST REPORT	12

APPENDICES

А	DIFFERENCES IN ANALYTICAL APPROACHES	
В	COMMENTS ON ANALYTICAL CRITERIA	
С	GUIDELINES AND STRATEGIES FOR SAMPLING	
D	SIMPLIFIED FLOWCHART FOR BULK ASBESTOS	
	SAMPLE IDENTIFICATION	
Е	BIBLIOGRAPHY	



This is a free preview. Purchase the entire publication at the link below:

Product Page

S Looking for additional Standards? Visit Intertek Inform Infostore

> Learn about LexConnect, All Jurisdictions, Standards referenced in Australian legislation